

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 4/00, 2/38, C07D 233/38	A2	(11) International Publication Number: WO 98/30601 (43) International Publication Date: 16 July 1998 (16.07.98)
(21) International Application Number: PCT/US98/00601 (22) International Filing Date: 7 January 1998 (07.01.98) (30) Priority Data: 60/034,727 10 January 1997 (10.01.97) US (71) Applicants (for all designated States except US): E.I. DUPONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). COMMONWEALTH SCIENTIFIC AND INDUSTRIAL RESEARCH ORGANIZATION [AU/AU]; Bayview Avenue, Clayton, VIC 3168 (AU). (72) Inventors; and (75) Inventors/Applicants (for US only): ANDERSON, Albert, G. [US/US]; 2410 St. Francis Street, Wilmington, DE 19808 (US). GRIDNEV, Alexei [US/US]; 113 Senatorial Drive, Greenville, DE 19807 (US). MOAD, Graeme [AU/AU]; 137 Monbulk Road, Kallista, VIC 3791 (AU). RIZZARDO, Ezio [AU/AU]; 26 Alex Avenue, Wheelers Hill, VIC 3150 (AU). THANG, San, Hoa [AU/AU]; 180 Clarinda Road, Clayton South, VIC 3169 (AU).		(74) Agent: COSTELLO, James, A.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US). (81) Designated States: AU, BR, CA, CN, JP, KR, MX, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: METHOD OF CONTROLLING POLYMER MOLECULAR WEIGHT AND STRUCTURE (57) Abstract <p>This invention concerns the preparation of polymers of low polydispersity and/or controlled molecular weight and architecture employing living free radical polymerization initiated by an alkoxyamine initiator or nitroxide plus, optionally, a free radical initiator; the polymer produced thereby; selected nitroxide and alkoxyamine initiators; and a process for making the initiators; the polymeric products being useful in protective coatings.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		


TITLE

METHOD OF CONTROLLING POLYMER MOLECULAR WEIGHT AND STRUCTURE

BACKGROUND OF THE INVENTION

5 This invention concerns the preparation of polymers with low polydispersity and/or controlled molecular weight and architecture by the use of living free radical polymerization initiated by an alkoxyamine or an appropriate nitroxide-initiator combination. It also concerns novel compounds useful in such
10 polymerizations and methods for their preparation.

Living radical polymerization based on the use of alkoxyamine initiators was invented by Rizzardo *et al* and is described in US Patent 4,581,429. Recent publications by Georges *et al* (Trends Polym. Sci., 1994, 2, 66-72), Hawker (J. Am. Chem. Soc., 1994, 116, 11185-11186) and others have described
15 the application of the methodology to the synthesis of narrow polydispersity polystyrenes. The nitroxide component in these latter studies is most often 2,2,6,6-tetramethylpiperidine-1-oxyl (TEMPO) or one of its derivatives. We have now discovered the advantages of nitroxide-mediated living free-radical polymerizations employing imidazoline nitroxides (1) as further defined hereafter:



Formula (1)


The characteristics of a living polymerization are discussed by Quirk and Lee (*Polymer International* 27, 359 (1992)) who give the following experimentally observable criteria:

- 25 1. Polymerization proceeds until all of the monomer has been consumed. Further addition of monomer results in continued polymerization.

2. The number average molecular weight (or the number average degree of polymerization) is a linear function of conversion.
3. The number of polymer molecules (and active centers) is a constant which is sensibly independent of conversion.
- 5 4. The molecular weight can be controlled by the stoichiometry of the reaction.
5. Narrow molecular weight distribution polymers are produced.
6. Block copolymers can be prepared by sequential monomer addition.
- 10 7. Chain end-functionalized polymers can be prepared in quantitative yield.

SUMMARY OF THE INVENTION

This invention provides a polymer of the Formula (2) below:



wherein:

R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups that are in a geminal position with respect to each other can together form a 4-8 membered ring; R groups that are in a cis position with respect to each other can together form a 4-8 membered ring;

X is selected from the group consisting of hydrogen, C_1 to C_{18} alkyl, substituted C_1 to C_{18} alkyl, C_6 to C_{18} aryl, C_6 to C_{18} substituted aryl; acyl; X and R can form a 5-8 membered ring; X and R^1 can form a 5-8 membered ring;

M is one or more monomer units selected from the group consisting of styrene,
 5 substituted styrene, alkyl acrylate, alkyl methacrylate, substituted alkyl acrylate, substituted alkyl methacrylate, acrylonitrile, methacrylonitrile, acrylamide, methacrylamide, N-alkylacrylamide, N-alkylmethacrylamide, N,N-dialkylacrylamide, N,N-dialkylmethacrylamide, isoprene and butadiene;
 n is an integer greater than 1;

10 Y is a residue derived from a species that initiates free radical polymerization or is selected from the group consisting of C_1 to C_{18} alkyl, substituted C_1 to C_{18} alkyl, C_1 to C_{18} alkoxy, substituted C_1 to C_{18} alkoxy, C_6 to C_{18} aryl, C_6 to C_{18} substituted aryl, C_6 to C_{18} aryloxy, C_6 to C_{18} substituted aryloxy, (C_1 to C_{18} alkoxy)carbonyloxy, (C_6 to C_{18} aryloxy)carbonyloxy, and sulfate radical anions;

15 and

all substituents are independently selected from the group that consists of epoxy, hydroxy, C_1 to C_{18} alkoxy, acyl, acyloxy, alkoxycarbonyl, aryloxy, cyano, silyl, halo, and C_1 to C_{18} dialkylamino.

The polymers of this invention have low polydispersity which
 20 provide improved flow properties in melt or solution. In addition, the presence of the nitroxyl end-group allows the formation of block copolymers by heating the preformed polymer with a different monomer. Alternatively, the nitroxyl end-group can be reduced or chemically modified to give a polymer with a more desirable end-group. The term "polymer(s)" employed herein includes block and
 25 graft copolymers and other complex architectures.

Specific monomers or comonomers from which M is derivable include the following:

methyle methacrylate, ethyl methacrylate, propyl methacrylate (all isomers), butyl methacrylate (all isomers), 2-ethylhexyl methacrylate, isobornyl methacrylate,
 30 methacrylic acid, benzyl methacrylate, phenyl methacrylate, methacrylonitrile, alpha-methylstyrene, methyl acrylate, ethyl acrylate, propyl acrylate (all isomers), butyl acrylate (all isomers), 2-ethylhexyl acrylate, isobornyl acrylate, acrylic acid,


- benzyl acrylate, phenyl acrylate, acrylonitrile, styrene, functional methacrylates, acrylates and styrenes selected from glycidyl methacrylate, 2-hydroxyethyl methacrylate, hydroxypropyl methacrylate (all isomers), hydroxybutyl methacrylate (all isomers), N,N-dimethylaminoethyl methacrylate,
- 5 N,N-diethylaminoethyl methacrylate, triethyleneglycol methacrylate, itaconic anhydride, itaconic acid, glycidyl acrylate, 2-hydroxyethyl acrylate, hydroxypropyl acrylate (all isomers), hydroxybutyl acrylate (all isomers), N,N-dimethylaminoethyl acrylate, N,N-diethylaminoethyl acrylate, triethyleneglycol acrylate, methacrylamide, N-methylacrylamide,
- 10 N,N-dimethylacrylamide, N-tert-butylmethacrylamide, N-n-butylmethacrylamide, N-methylolmethacrylamide, N-ethylolmethacrylamide, N-tert-butylacrylamide, N-n-butylacrylamide, N-methylolacrylamide, N-ethylolacrylamide, vinyl benzoic acid (all isomers), diethylaminostyrene (all isomers), alpha-methylvinyl benzoic acid (all isomers), diethylamino alpha-methylstyrene (all isomers). p-vinylbenzene
- 15 sulfonic acid, p-vinylbenzene sulfonic sodium salt, trimethoxysilylpropyl methacrylate, triethoxysilylpropyl methacrylate, tributoxysilylpropyl methacrylate, dimethoxymethylsilylpropyl methacrylate, diethoxymethylsilylpropylmethacrylate, dibutoxymethylsilylpropyl methacrylate, diisopropoxymethylsilylpropyl methacrylate, dimethoxysilylpropyl methacrylate,
- 20 diethoxysilylpropyl methacrylate, dibutoxysilylpropyl methacrylate, diisopropoxysilylpropyl methacrylate, trimethoxysilylpropyl acrylate, triethoxysilylpropyl acrylate, tributoxysilylpropyl acrylate, dimethoxymethylsilylpropyl acrylate, diethoxymethylsilylpropyl acrylate, dibutoxymethylsilylpropyl acrylate, diisopropoxymethylsilylpropyl acrylate,
- 25 dimethoxysilylpropyl acrylate, diethoxysilylpropyl acrylate, dibutoxysilylpropyl acrylate, diisopropoxysilylpropyl acrylate, maleic anhydride, N-phenylmaleimide, N-butylmaleimide, butadiene, isoprene, chloroprene.

This invention provides a process for preparing the polymers of Formula (2) comprising contacting reactant (i) with one or both of reactants (ii)

30 and (iii) wherein:


(i) is at least one monomer M;

(ii) is at least one imidazoline nitroxide of the formula



and a source of free radicals $Y\cdot$; and

(iii) is at least one alkoxyamine selected from the formula



5

wherein:

R , R^1 , R^2 , R^3 , X , M and Y are defined above;

Z is a group having at least one carbon atom such that the carbon centered radical $Z\cdot$ is capable of initiating free-radical polymerization of monomer (M); Y

10 and the reaction conditions are selected so that the $Y(M)_n-O$ moiety in the compounds of Formula (2) formed from reactants (i) and (ii) undergo facile homolysis; Z and the reaction conditions are selected so that the $Z-O$ moiety and the $Z(M)_n-O$ moiety formed by reacting (i) with (iii) undergo facile homolysis; n is an integer of 1 or greater; and $Y\cdot$ can be produced thermally from the monomer

15 (when one of the monomers is styrene or a styrene derivative) or from a free-radical initiator or combination of initiators.

Use of the nitroxides of Formula 1 (or the corresponding alkoxyamines) offers significant advantages over nitroxides previously employed in nitroxide-mediated polymerization: homopolymers, statistical copolymers and

20 block copolymers which have controlled molecular weight, a narrow molecular weight distribution and a defined end-group functionality can be synthesized. The

method is also adaptable to the preparation of multi-block and graft and other polymers of more complex architecture. With appropriate selection of the substituents, R, R¹, R², R³, and X, (defined hereafter), the use of the nitroxides (1) offers lower polydispersities and better living character than, for example,

5 TEMPO and derivatives.

Further advantages are that (a) the nitroxides (1) and the derived alkoxyamines are synthesized from readily available precursors by a simple experimental route; (b) they are subject to fewer side reactions (e.g., disproportionation of propagating radical with nitroxide or chain transfer to nitroxide); and (c) they are involatile. This provides an advantage over many of

10 the most commonly used nitroxides such as TEMPO and many of its derivatives, and di-t-butyl nitroxide, which are odorous.

The process can be run continuously or in batch and can be carried out as a solution, emulsion, suspension or bulk polymerization using procedures

15 well known in the art.

If Z is a polymer chain (e.g., Y(M)_n-) then the product can be a block copolymer. Block copolymers can also be prepared by the sequential addition of different monomers or monomer combinations. Graft copolymers and polymers of more complex architecture can be prepared from appropriately

20 designed precursors containing multiple nitroxide moieties.


Polymerization reaction conditions include temperatures in the range of about 20°C to 300°C, preferably between 40°C to 250°C, and most preferably between 50°C to 150°C, ambient pressures up to 100 atmospheres and optional solvent(s) compatible with the monomer/polymer systems.

25 The polymers made by the process in this invention are also characterized by possessing functional end groups which are derived from the moieties Y and/or Z and the nitroxide fragment (1). Such functionality will include hydroxy; carboxylic acid (-COOH) and its esters; cyano; isocyanato; epoxy; halo; amino; and the like.

30 This invention concerns particular nitroxides of the Formula (1) useful in the polymerization process wherein:


R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups in a geminal position with respect to each other can together form a 4-8 membered ring; and R groups in a cis position with respect to each other can together form a 4-8 membered ring; and
 5 X is selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; acyl; X and R can form a 5-8 membered ring; and X and R³ can form a 5-8 membered ring; with the proviso that R, R¹, R², R³ and X are not all methyl.

10 Preferred nitroxides selected from the group above are the following:



Formula (4)

where X is selected from the group consisting of alkyl, optionally substituted alkyl, benzyl; and



Formula (5)

15

where X is alkyl of C₁ to C₁₈.

This invention also concerns novel alkoxyamines of the Formula (3) wherein:

R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups in a geminal position with respect to each other can together form a 4-8 membered ring, and R groups in a cis position with respect to each other can together form a 4-8 membered ring;

X is selected from the group consisting of hydrogen, C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; acyl; X and R can form a 5-8 membered ring; and X and R³ can form a 5-8 membered ring; and

Z is a group having at least one carbon atom and the carbon centered radical Z• is capable of initiating free radical polymerization of the monomer (M).

Suitable Z groups are -C(Me)₂Ph, -C(Me)₂CN, -C(Me)(CN)CH₂CH(Me)₂, -C(Me)(CN)(substituted alkyl), -C(Me)₂CO₂Alkyl, -C(Me)₂CO₂H, -C(Me)₂CH₂C(Me)₃, -C(Me)₃, -C(Me)HPh and Y(M)_n.

This invention also includes a process for making the nitroxides of Formula (1). The process comprises reacting an aminonitrile and a ketone to form a cyanoimine, and reacting said imine with hydrogen sulfide to produce a linear thioamide, and cyclizing said linear thioamide to form a 2,2,5,5,-tetrasubstituted-imidazolidin-4-thione, and converting the cyclic thioamide to the corresponding cyclic amide and then converting the final imidazolidine-4-one to the nitroxide.


In particular, the process for making nitroxides of Formula (1) involves: (i) preparing a colorless aqueous ammonium sulfide solution containing sodium thiocyanate by titrating an aqueous ammonium sulfide solution containing ammonium polysulfide with sodium cyanide under nitrogen; (ii) sequentially adding an aminonitrile and a ketone to the aqueous ammonium sulfide solution under nitrogen; (iii) adding base and then neutralizing; and (iv) oxidizing the reaction product of step (iii) to form the nitroxide.

Alternatively, in process step (ii) aminonitrile can be replaced by a mixture of ketone, ammonium chloride, and sodium or potassium cyanide. In another embodiment of this process, the process is stopped before addition of sodium tungstate and the corresponding cyclic amine/amide is isolated. Process step (ii) can be performed at a temperature of between 20° and 80°C, preferably


between 30° and 60°C, and most preferably at 54°C. The base is preferably sodium carbonate or sodium hydroxide, most preferably sodium hydroxide. Any convenient acid can be used for the neutralization, the preferred acid is sulfuric acid. In this process, the concentration of hydrogen peroxide is preferably 20 to 50%, most preferably 30%. The preferred oxidants for the amine to nitroxide transformation are H₂O₂/tungstate, dimethyldioxirane, H₂O₂/acetic acid.

DETAILS OF THE INVENTION

The most commonly used nitroxides in nitroxide-mediated living free-radical polymerizations have been 2,2,6,6-tetramethylpiperidin-N-oxyl (TEMPO) and derivatives of this compound and di-t-butyl nitroxide (diBuNO).



TEMPO



diBuNO

These and other nitroxides/alkoxyamines that are conventionally used in nitroxide-mediated living free-radical polymerizations are inherently of high cost. Substantial cost improvements for the overall process can therefore be achieved by the use of nitroxide (1), a material obtainable from inexpensive precursor by a simple experimental route.

It has been found, that in various polymerizations, the use of certain 2,2,5,5-tetraalkylimidazolin-4-one-1-oxyl derivatives in nitroxide-mediated polymerization offer lower polydispersities for polymers than is obtained with other nitroxides used for this purpose (e.g., TEMPO and derivatives, or diBuNO).





In the context of the present invention, low polydispersity polymers are those with polydispersities that are significantly less than those produced by conventional free radical polymerization. In conventional free radical polymerization, polydispersities (the polydispersity is defined as the ratio of the weight average and number average molecular weights - \bar{M}_w/\bar{M}_n) of the polymers formed are typically in the range 1.6-2.0 for low conversions (<10%) and can be substantially greater than this for higher conversions. Polydispersities


obtained with the present invention are usually less than 1.5, often less than 1.3 and, with appropriate choice of the nitroxides (1) / alkoxyamines and the reaction conditions, can be less than 1.1. The low polydispersity can be maintained at high conversions.

5 Polydispersities in nitroxide-mediated polymerization are believed to depend on a number of factors. These include (i) the rate of exchange between active and dormant species which is largely determined by the rate of bond homolysis between N-O and the adjacent moiety for the alkoxyamines involved either as initiator species or formed during the polymerization (for a discussion on
10 this subject see Moad and Rizzardo, *Macromolecules* 1995, 28, 8722-8); and (ii) the significance of various side reactions.


For polymerizations involving nitroxides (1) the rate of bond homolysis between N-O and the adjacent moiety and polydispersities obtained depend on the particular nitroxide or alkoxyamine used and in particular on the
15 substituents R, R¹, R², R³ and X. A preferred group of nitroxides in this context are the N-alkyl-2,2,5,5-tetraalkylimidazolin-4-one-1-oxyl compounds (i.e., (1) X=alkyl, for example, 2,5-bis(spirocyclohexyl)-3-methylimidazolidin-4-one-1-oxyl (NO-88-Me)) which are seen to offer the lowest polydispersities in styrene polymerizations or copolymerizations. Also preferred within each class (X=alkyl
20 and X=H) are those (1) with more bulky R-R³.

The following are structures of nitroxides described herein:





NO-67-Bn




NO-67-nBu

It is believed that an important side reaction in nitroxide-mediated polymerization is disproportionation between the nitroxide and the propagating species. It has been found that in methyl methacrylate (MMA) polymerization the use of 2,2,5,5-tetraalkylimidazolin-4-one-1-oxyl derivatives offer low polydispersities and good living character for polymerizations.

While not wishing to be bound by a particular mechanism, these advantages are believed to be in part a consequence of the 5-membered ring imidazoline nitroxides providing a higher combination: disproportionation ratio for the reaction with propagating radicals than 6-membered ring (i.e., TEMPO) or open chain nitroxides (i.e., diBuNO). These pathways are illustrated in Scheme 1 for MMA polymerization. Note that the products of the disproportionation reaction, vinyl terminated macromonomer and hydroxylamine (H-Q) can also react further under polymerization reaction conditions leading to further complications. Clearly, minimization of this side reaction is important to obtaining polymerization with living characteristics.

Scheme 1



In Scheme 1, Q is a nitroxide.


Similar side reactions have also been shown to occur during nitroxide-mediated styrene polymerization. In styrene polymerization at 90°C, the rate constants for hydrogen transfer from the propagating species to NO-67 and TEMPO relative to the rate constant of propagation have been measured as 0.18 and 0.43 respectively.

In the synthesis of nitroxides of Formula (1), the product nitroxide can be isolated by conventional means, preferably from the reaction mixture by filtration or by extraction with an organic solvent that is substantially insoluble in water.

It has been found that the ammonium polysulfide reacts with either aminonitrile or cyanide ion, thereby reducing the amount of cyanide below stoichiometric proportions thus lowering the overall yield. This can be prevented by prior addition of cyanide ion to the point of decolorization of the polysulfide and formation of harmless thiocyanate.

The procedure disclosed herein for synthesis of nitroxides (1, X=H) is as follows:

SCHEME 2



The alkoxyamines of this invention are made from the compounds
 of Formula (1) by combining them with Z• for example by the procedure of
 Example 43 and by that described in *Macromolecules*, 1997, 30, 6445-6450. The
 alkoxyamines of this invention can be made by a variety of methods such as
 alkylating the derived hydroxylamines or nitroxides of Formula (1); and
 alkoxyating the compound of Formula (6) as will be obvious to one skilled in the
 art.

EXAMPLESGeneral Experimental Conditions

Monomers were purified (to remove inhibitors) and flash distilled
 immediately prior to use. Degassing was accomplished by repeated freeze-
 evacuate-thaw cycles. Once degassing was complete ampoules were flame sealed
 under vacuum and completely submerged in an oil bath at the specified
 temperature for the specified times. The percentage conversions were calculated
 gravimetrically.

The structures of polymers and block copolymers have been
 verified by application of appropriate chromatographic and spectroscopic
 methods. Gel permeation chromatography (GPC) has been used to establish the
 molecular weight and molecular weight distribution (polydispersity) of the
 polymers. A Waters Associates liquid chromatograph equipped with differential

refractometer and 10^6 , 10^5 , 10^4 , 10^3 , 500 and 100 Å Ultrastyrigel columns was used. Tetrahydrofuran (flow rate of 1.0 ml/min) was used as eluent. The molecular weights are provided as polystyrene equivalents. The terms M_n , M_w and \bar{M}_w/\bar{M}_n are used to indicate the number and weight average molecular weights and the polydispersity respectively. NMR spectroscopy was used to elucidate the structures of polymers and provide evidence for the polymers' end-groups. NMR spectra were obtained on a Bruker (200 MHz) spectrometer and $CDCl_3$ was used as solvent.

Examples 1-5

Styrene polymerization

These examples show that narrow polydispersity polystyrene can be prepared with NO-88. Polydispersity is initially 1.3 and is reduced to 1.2 over the course of the experiment.

Procedure:

A stock solution contained styrene (9.10 g, 87.5 mmol), benzoyl peroxide (70.7 mg, 0.29 mmol) was prepared. NO-88 (29.1 mg, 0.12 mmol) was added separately to each of 5 ampoules. An aliquot (2 ml) of the stock solution was then added to each ampoule, and the contents of the ampoules were degassed by three freeze-evacuate-thaw cycles, sealed and heated at 130°C for the designated times. The results are shown in Table 1.

Table 1: Bulk Styrene Polymerization in the presence of NO-88 and benzoyl peroxide at 130°C.

Example	Time/h	\bar{M}_n	\bar{M}_w/\bar{M}_n	\bar{M}_n (calc) ^a	% Conv. ^b
1	2	508	1.31	235	1.5
2	4	1626	1.27	784	5.0
3	8	4911	1.26	5334	34.0
4	23	7061	1.21	10559	67.3
5	72	12291	1.20	14136	90.1

^a \bar{M}_n (calc) = [monomer converted]/([BPO] x 2)

^b % conversion evaluated from ¹H NMR spectra.

Examples 6-11**MMA Polymerizations**

The following section reports results of methyl methacrylate polymerizations in the presence of the azo-initiator, 2,2'-Azobis(2,4-dimethylvaleronitrile) (Vazo®-52) and different nitroxides. The results for NO-67 (Examples 6-9) and NO-88 (Examples 10-12) are shown in Tables 2 and 3 respectively. The effectiveness of these nitroxides is compared with other nitroxides in Table 4. Further sampling after one hour of reaction time shows little or no increase in molecular weight or conversion. The five-membered ring nitroxides (NO-67 and NO-88) gave the most favorable results (narrowest polydispersity). In all cases, the product is believed to be a MMA macromonomer formed by loss of a hydrogen atom from the propagating species to the nitroxide (i.e., reaction by disproportionation rather than combination).

Procedure:

A stock solution was prepared containing MMA (10 ml, 9.36 g) Vazo®-52 (13.43 mg, 0.054 mmol), and NO-67 (14.2 mg, 0.077 mmol). 3 ml of the stock solution was transferred to each of three ampoules which were then degassed through 3 freeze-thaw cycles, sealed, and heated at 90 °C for the indicated times.

Table 2: Bulk MMA Polymerization with Vazo®-52 and NO-67, 90°C.

Example	time/h	\bar{M}_n	\bar{M}_w/\bar{M}_n	% Conv. ^a	calc. \bar{M}_n
6	0.5	31737	1.68	24.9	30305
7	1	38021	1.47	25.3	30730
8	6	35709	1.57	38.2	46411

^a % conversion evaluated from mass of polymer obtained.

Procedure:

A stock solution was prepared containing MMA (9 ml, 8.42 g) Vazo®-52 (12.08 mg, 0.049 mmol), and NO-88 (17.16 mg, 0.069 mmol). 3 ml of the stock solution was transferred to each of three ampoules which were then degassed through 3 freeze-thaw cycles, sealed, and heated at 90 °C for the indicated times.




Table 3: Bulk MMA Polymerization with Vazo®-52 and NO-88, 90°C.

Example	time/h	\bar{M}_n	\bar{M}_w/\bar{M}_n	% Conv. ^a	calc. \bar{M}_n
9	0.5	308	1.03	0.7	866
10	1	6472	1.44	6.4	7822
11	6	7890	1.44	5.4	6590






^a % conversion evaluated from mass of polymer obtained.

5

TABLE 4**Table 4:** MMA Polymerizations after 1 hour at 90°C with VAZO®-52 and Nitroxideⁱ

Nitroxide	\bar{M}_n	%Conv.	Calculated \bar{M}_n	\bar{M}_w/\bar{M}_n
 NO-88	6472	6.4	7822	1.44
 NO-67	38021	24.9	30730	1.47
	18294	18.4	21528	1.71

ⁱ Reaction conditions similar to those used for experiments described in Tables 2 and 3.

TEISO				
	10515	11.2	13554	2.24
 TEMPO	22073	14.3	17322	3.11
	16959	17.5	21181	3.30
 DiBuNO	41904	15.4	18696	3.15
	19191	17.9	21735	4.10

VAZO® is a registered trademark of E. I. du Pont de Nemours and Company. The particular VAZO® compositions referred to herein comprise the following compounds:

- 5 VAZO®52 2,2'-azobis(2,4-dimethylvaleronitrile),
 VAZO®64 2,2'-azobisisobutyronitrile,
 VAZO®67 2,2'-azobis(2-methylbutyronitrile), and
 VAZO®88 1,1'-azobis(cyanocyclohexane).

Examples 12 to 27**Styrene polymerization**

A series of styrene polymerizations was conducted in the presence of NO-67, NO-88, and the N-substituted imidazolidinone nitroxides, NO-67-Me, NO-88-Me, NO-67-Bn and NO-67-nBu) and benzoyl peroxide initiator. The
5 polymerization was carried out at 130°C for a period of times indicated in Table 5 below. Results are summarized in Table 5.

Procedure:

10 The following six solutions were prepared.

(i) Styrene (5 ml), NO-88 (72.75 mg) and benzoyl peroxide (35.35 mg).

(ii) Styrene (10 ml), NO-88-Me (154.00 mg) and benzoyl peroxide (70.70 mg).

(iii) Styrene (5 ml), NO-67 (56.75 mg) and benzoyl peroxide (35.35 mg).

(iv) Styrene (10 ml), NO-67-Me (122.00 mg) and benzoyl peroxide (70.70 mg).

15 (v) Styrene (5 ml), NO-67-Bn (84.32 mg) and benzoyl peroxide (35.35 mg).

(vi) Styrene (5 ml), NO-67-nBu (73.88 mg) and benzoyl peroxide (35.35 mg).

Aliquots (2 ml) of these solutions were transferred into ampoules and the contents were degassed by three freeze-thaw cycles. The ampoules were then sealed and heated at 130°C for times indicated in Table 5. The ampoules were
20 cooled, opened and the reaction mixture reduced *in vacuo* to a residue which was dried to constant weight and analyzed by GPC.

Table 5: GPC molecular weight data of polystyrene prepared via polymerizations of styrene with nitroxides and benzoyl peroxide at 130 °C

Example	Nitroxides	Time/hr	\bar{M}_n	\bar{M}_w/\bar{M}_n	% Conv.
12	NO-88	23	16047	1.23	99.0
13	NO-88-Me	2	780	1.18	5.9
14	NO-88-Me	4	3115	1.13	20.9
15	NO-88-Me	8	8765	1.09	56.0
16	NO-88-Me	18	16271	1.09	96.0
17	NO-88-Me	23	16300	1.09	99.0
18	NO-67	23	16043	1.49	99.0
19	NO-67-Me	2	502	1.36	5.0
20	NO-67-Me	4	1380	1.29	9.9
21	NO-67-Me	8	2499	1.34	22.4
22	NO-67-Me	18	4693	1.29	49.4
23	NO-67-Me	23	8075	1.24	60.0
24	NO-67-Bn	4	1402	1.23	9.1
25	NO-67-Bn	18	5102	1.28	47.4
26	NO-67-nBu	4	1430	1.22	8.8
27	NO-67-nBu	18	6013	1.25	53.0

5 The proton-NMR spectrum of a polystyrene sample (\bar{M}_n 3115) of Example 14 had signal at δ 2.90 ppm clearly indicating the presence of the N-methyl of the 2,5-bis(spirocyclohexyl)-3-methylimidazolidin-4-one-1-oxyl (NO-88-Me) end group.

Examples 28 -31

Acrylate Polymerization

10 Polymerization of *tert*-butyl acrylate was carried out in sealed tubes at 120°C using the alkoxyamine, 1-(2-*tert*-butoxy-1-phenylethoxy)-2,5-bis(spirocyclohexyl)-3-methylimidazolidin-4-one as initiator-terminator. This

example demonstrates the acrylate polymers with low polydispersity (1.3-1.4) can be obtained.

Two set of experiments were conducted:

- (i) A stock solution of the alkoxyamine (71.3 mg), tert-butyl acrylate (1.0 ml) in benzene (4.0 ml) was prepared. Aliquots (2.0 ml) were transferred into ampoules (x2) and the contents were degassed by three freeze-thaw cycles. The ampoules were then sealed and heated at 120°C for 24 hours and 49 hours respectively. Results are shown in Table 6 below.

Table 6: *tert*-Butyl acrylate polymerizations in the presence of alkoxyamine in benzene at 120°C

Example	Time (hr)	\bar{M}_n	\bar{M}_w/\bar{M}_n	% Conv.
28	24	1525	1.39	28.0
29	49	1830	1.32	34.4

The proton-NMR spectrum of a sample of poly(*tert*-butyl acrylate) of Example 28 (\bar{M}_n 1525) had signals at δ 7.10 ppm indicating the presence of phenyl group (cf. δ 7.30 ppm for the original alkoxyamine used) and δ 2.90 ppm indicating the presence of the N-methyl group of the NO-88-Me.

- (ii) A stock solution of alkoxyamine (71.3 mg), *tert*-butyl acrylate (5.0 ml) was prepared. Aliquots (2.0 ml) were transferred into ampoules (x2) and the contents were degassed by three freeze-thaw cycles. The ampoules were then sealed and heated at 120°C for 24 hours and 49 hours respectively. Results are shown in Table 7 below.

Table 7: Bulk *tert*-Butyl acrylate polymerizations in the presence of alkoxyamine at 120°C

Example	Time (hr)	\bar{M}_n	\bar{M}_w/\bar{M}_n	% Conv.
30	24	8272	1.51	28.6
31	49	9005	1.41	39.8

Examples 32 - 33

Block Copolymer Syntheses

- The following two examples [polystyrene-*block*-poly(4-methylstyrene) and polystyrene-*block*-poly(*n*-butyl acrylate)] demonstrate the synthesis of block copolymers. The samples were prepared by heating a narrow polydispersity polystyrene (derived from NO-88-Me) (\bar{M}_n 8765, \bar{M}_w/\bar{M}_n 1.09; see

Table 5, Example 15) with 4-methylstyrene and n-butyl acrylate respectively. Results are excellent in both cases and give low polydispersity block copolymers.

Example 32

5 **Polystyrene-*block*-poly(4-methylstyrene)**

To an ampoule, a sample of polystyrene (250 mg) (\bar{M}_n 8765, \bar{M}_w/\bar{M}_n 1.09; Example 15) was dissolved in 1 ml of 4-methylstyrene (freshly distilled). The contents of the ampoule was degassed and sealed under vacuum. Subsequently, the mixture was polymerized at 130°C for 18 hours and
10 gave a narrow polydispersity polystyrene-*block*-poly(4-methylstyrene) (0.85g, 95% conversion), \bar{M}_n 36872, \bar{M}_w/\bar{M}_n 1.14.

Example 33

15 **Polystyrene-*block*-poly(n-butyl acrylate)**

To an ampoule, a sample of polystyrene (250 mg) (\bar{M}_n 8765, \bar{M}_w/\bar{M}_n 1.09; Example 15) was dissolved in 1 ml of n-butyl acrylate (freshly distilled). The contents of the ampoule was degassed and sealed under vacuum. Subsequently, the mixture was polymerized at 130°C for 18 hours and
20 gave a narrow polydispersity polystyrene-*block*-poly(n-butyl acrylate) (0.608g, 68% conversion), \bar{M}_n 21526, \bar{M}_w/\bar{M}_n 1.29.

Examples 34-36

Statistical Copolymer Syntheses

A series of styrene/acrylonitrile (62:38 molar ratio; the azeotropic
25 composition) copolymerizations in the presence of N-substituted imidazolidinone nitroxides NO-88-Me, NO-67-Me and NO-67-Bn. The experiments were conducted thermally at 130 °C for 18 hours. Results are summarized in Table 8.

Procedure:

30 A stock solution (I) of freshly distilled styrene (7.27g) and acrylonitrile (2.27g) was prepared. Each ampoule contains stock solution (2g) and nitroxide (1.23×10^{-4} mol). The content was degassed, sealed and heated at 130°C for 18 hours.

Table 8: GPC data of styrene/acrylonitrile copolymers prepared thermally at 130°C with different nitroxides.

Example	Nitroxide	\bar{M}_n	\bar{M}_w/\bar{M}_n	% Conv.
34	NO-88-Me	23098	1.16	>95.0
35	NO-67-Me	17035	1.34	84.0
36	NO-67-Bn	17605	1.35	89.0

Examples 37-42

5

Syntheses of Nitroxides of Formula (1)

The following Examples 37-38 illustrate the novel process for synthesis of nitroxides (1, where X=H).

Example 37

10 Preparation of 2,5-diethyl-2,5-dimethylimidazolidin-4-one-1-oxyl (NO-67)

Preparation of 2,5-diethyl-2,5-dimethylimidazolidin-4-thione

A 1 liter 4-necked round-bottomed flask equipped with a mechanical stirrer, thermocouple thermometer, nitrogen bubbler, bleach-filled scrubber, and reflux condenser was charged with 17.4 g ammonium chloride (0.32 mol), 35.9 g AN-67 (0.3 mol, 87% 2-amino-2-methylpropionitrile in water, ¹H NMR (ppm) of freshly distilled AN-67 in D₂O: 1.03 (t, 3H), 2.45 (s, 3H), 1.75 (q, 2H), 23.1 g 2-butanone (0.32 mol), and 132.9 g of 20% ammonium sulfide solution (0.39 mol). As the solution was heated to 50°C, a slight exotherm occurred that increased the temperature to 65°C and some ammonium hydrosulfide sublimed into the condenser. After 20 minutes, the temperature declined to 55°C and was held there for 18 hours. An oily liquid layer forms on top of the aqueous solution during the first 5 minutes. The yellow polysulfide color is discharged in the first minute; this is caused by reaction of cyanide ion with sulfur to give colorless thiocyanate ion and a decrease in yield. The next day, the solution was cooled to -15°C, 25 g of NaCl added to salt out the thione, and filtered cold to give 39 g of product. The mother liquor was treated with 10 g of K₂CO₃ to precipitate an additional 5 g of product. K₂CO₃ is more effective at salting out thiones, amides, and nitroxides than NaCl. The solids were combined

to give 44 g (80% yield) of thione after 2 days of air drying, mp. 58-64°C. IR (nujol) 1540 cm⁻¹; ¹H NMR ppm (D₂O) 0.96 (overlapping t, 12H, CH₃ on 4 ethyls), 1.39, 1.40, 1.42, 1.43 (4 singlets, total of 12H, CH₃ for four isomers, i.e., 2 cis-trans pairs), 1.75 (m, 8H, 4 CH₂ groups).

5	combustion analysis:	calcd. for C ₉ H ₁₈ N ₂ S·0.1(H ₂ O)	obs.
	C	57.46	57.90
	H	9.75	9.24
	N	14.89	14.94
	S	17.05	16.68

10 The thione can be purified by column chromatography on silica gel using hexane to elute an odorous fraction before the thione. The effect of variation of temperature and concentration of the reactants on yield and reaction rate was examined in a sealed NMR tube using D₂O as a solvent and sodium tosylate as an internal standard. What was observed was a smooth decrease in
 15 concentration of starting materials and smooth increase in concentration of product. The reaction time can be reduced from 16 hours at 50°C to 6 hours at 80°C. The compound, 2-methyl-2-aminobutyrothioamide, was not observed indicating that this alicyclic intermediate reacts with MEK in a fast step to yield the cyclic product.

20 Preparation of 2,5-diethyl-2,5-dimethylimidazolidin-4-one

A 5 liter 4-necked round-bottomed flask equipped with a mechanical stirrer and thermocouple thermometer was charged with 250 ml water and 43.3 g (0.232 mol) of 2,5-diethyl-2,5-dimethylimidazolidin-4-thione. In order to make the thione dissolve, 1.8 g NaOH was added. The solution was cooled to
 25 0-2°C with a dry ice-acetone bath. The flask was fitted with two additional funnels. Simultaneously, a solution of 16.7 g NaOH in 100 ml water (total of 18.5 g or 0.464 mol of NaOH used) was added through one of the funnels and 105 ml (0.928 mol) of 30% H₂O₂ was added through the other funnel. The reaction mixture was stirred rapidly and required extensive cooling during the addition.
 30 The 5 liter flask was used to provide a large surface area for efficient cooling of the exothermic reaction. The heat of reaction was 269.2 Kcal/mol; 124. The addition was completed in 2 hours; the mixture was stirred an additional half hour.

At the end of this time, TLC indicated that no thione remained. Then, 27.9 g of NaHSO₃ (0.172 mol) was added to quench excess peroxide; this reaction is also somewhat exothermic (temperature increases from 26 to 43°C). The reaction mixture was transferred to a 2 liter round-bottomed flask and the solvent removed with a rotary evaporator (aspirator pressure) to give a white residue. The residue was extracted with 850 ml of boiling ethanol. Then, 50 ml of toluene was added to the solution and 130 ml of water/ethanol/toluene azeotrope distilled to remove any remaining water. The solution was cooled and filtered to remove a small amount (~ 1 g) of Na₂SO₄ and then the ethanol was removed on the rotary evaporator to give a syrup that crystallized on cooling to room temperature. The yield was 37.5 g (95%) mp 58-64°C. IR (nujol) 1705, 1659 cm⁻¹. ¹H NMR (CDCl₃ + D₂O) ppm (combination of equal amounts of 2 sets of cis-trans pairs) 0.95-0.98 (m, 12H, CH₃ on 4 ethyls), 1.27, 1.31, 1.34, 1.38 (4 s, total 12H, 4 CH₃), 1.50-1.70 (m, 8H, CH₂ on 4 ethyls). The singlets at 1.34 and 1.38 collapse to a singlet in D₂O but now integrate 6H.

combustion analysis:	calcd. for C ₉ H ₁₈ N ₂ O	obs.
C	63.49	63.07
H	10.66	10.01
N	16.45	16.23
O	9.40	9.49

Preparation of 2,5-diethyl-2,5-dimethylimidazolidin-4-one-1-oxyl

A one liter polymer jar equipped with a mechanical stirrer, bleach filled odor trap, heating mantel, reflux condenser, and thermocouple thermometer was charged with 153.3 g (0.45 mol) 20% ammonium sulfide solution. To this solution was added 1.47 g (0.03 mol) NaCN to react with the ammonium polysulfide impurity in the ammonium sulfide solution. Then, 35.9 g AN-67 (0.3 mol) and 21.7 g 2-butanone (0.3 mol) was added. The solution was stirred and heated under nitrogen at 55°C for 18 hours; some ammonia was evolved. Two liquid layers form; the lower layer is thioamide. The volume of the reaction mixture is now 200 ml. The mixture was cooled to room temperature and a solution of 36 g NaOH (0.9 mol) in 100 ml water was added. The solution was

cooled to 0°C and 306 g (2.7 mol) 30% H₂O₂ added dropwise with stirring and cooling at 4-10°C. The addition took 65 minutes. After stirring for one hour, the solution was brought to pH = 7 by addition of a solution of 58 g concentrated H₂SO₄ and 56 g of water at 13°C. Then, 68 g (0.6 mol) of 30% H₂O₂ was added.

5 No exotherm was noted at this time. To this was added 5.0 g Na₂WO₄·2H₂O. The total reaction volume is 763 ml. An initial greenish-yellow color (pertungstate ion) is replaced by a deeper yellow color (nitroxide). The temperature of the mixture climbs from 13 to 31°C over 3-1/2 hours. The next day, the solution was filtered to give 27.5 g (40% yield) of nitroxide, mp 117-122°C. It was

10 subsequently found that 1/3 of the AN-67 is destroyed by hydrolysis and irreversible reaction with sulfur to form thiocyanate ion. If this is taken into account, the yield is 82%; each step is about 93%. The solubility in NMP is at least 1:1. IR (nujol) 1720, 1675 cm⁻¹; (toluene solution) 1713.3 cm⁻¹. The nitroxide displays a triplet in the ESR. Aliquots of reaction mixture were

15 withdrawn at selected times and diluted with a known amount of xylene. The integrated intensity of the ESR triplet was plotted as a function of time when the concentration of peroxide was doubled or the concentration of tungstate ion was increased to three. The data were fitted to parabolas. The initial slopes of the lines are obtained by differentiating the empirically fitted curves to determine the

20 slope of the line and solving the equation so obtained at x = 0; the rate law at 24°C was found to be $K = k[H_2O_2]^{0.5+0.1}[WO_4^{2-}]^{1.0+0.1}$

	combustion analysis:	calcd. for C ₉ H ₁₇ N ₂ O ₂ ·0.03(CH ₂ Cl ₂)	obs.
	C	57.75	57.71
	H	9.16	8.82
25	N	14.92	15.21
	O	17.04	17.28

Example 38

Preparation of 2,5-bis(spirocyclohexyl)imidazolidin-4-one-1-oxyl (NO-88)

30 Preparation of 2,5-bis(spirocyclohexyl)imidazolidin-4-thione.

A 2 liter 4-necked round-bottomed flask equipped with a mechanical stirrer, heating mantel, reflux condenser, thermocouple thermometer,

nitrogen bubbler and exit tube connected to a bleach filled odor trap was charged with 132.9 g (0.39 mol) of 20% ammonium sulfide solution followed by 0.5 g NaCN to decolorize the polysulfide impurity in the ammonium sulfide solution. Under a positive nitrogen flow, 16.1 g (0.3 mol) of ammonium chloride and 14.7 g (0.3 mol) of NaCN was added. The temperature of the solution dropped to 8°C. Then, 58.9 g (0.6 mol) of cyclohexanone that had previously been deoxygenated by bubbling nitrogen through it for 10 minutes was added dropwise while stirring during 25 minutes. The temperature rose to 30°C. The temperature of the solution was increased to 47°C, at which point external heating was stopped and the reaction spontaneously allowed to exotherm to 63°C. The temperature was then maintained at 55°C. After 1 hour, 1.0 g NaCN was added and a mild exotherm to 63°C followed by a return to 55°C was noted. An additional 1.0 g NaCN was added 30 minutes later; this caused only a mild exotherm to 58°C. The temperature was held at 55°C overnight. A sample of the resulting slurry was then withdrawn and divided into two parts. One part was dissolved in acetone, and checked by TLC (9:1 CH₂Cl₂:acetone); two species were present. The other part was filtered to give white crystals, mp 225-230°C. The precipitate was filtered in place with a filter stick to avoid handling the odorous mixture. The insoluble precipitate was thione; the other impurity was cyclohexanone, which remained in the filtrate. The thione was washed by adding 300 ml of water to the flask, stirring, and then removing the water through the filter stick. IR (nujol) 1520 cm⁻¹.

Preparation of 2,5-bis(spirocyclohexyl)imidazolidin-4-one

To the wet crystalline residue obtained above was added in the same flask 24 g (0.6 mol) of NaOH dissolved in 300 ml of water. The crystals failed to dissolve; the crystals were finally dissolved by addition of 485 ml of methanol. The solution does not show the characteristic exotherm upon addition of 30% hydrogen peroxide at 0-5°C. The temperature of the solution was increased to 40°C; at this temperature addition of peroxide is exothermic. After adding 147 g (4x0.32 mol) of 30% peroxide, the solution temperature was held at 55°C for 30 minutes and then stirred at room temperature overnight; by TLC, the mixture consisted of amide and thione. The mixture was filtered and the

precipitate washed with 3x100 ml of water. To the filtrate was added 57 g of peroxide [total peroxide used = 204 g (1.8 mol)] and the solution was warmed to 40°C. A slight exotherm to 46°C occurred. To aid the oxidation, 1 g of $\text{Na}_2\text{WO}_4 \cdot 2\text{H}_2\text{O}$ was added. After 15 minutes, a white precipitate began to deposit.

- 5 The mixture was allowed to stir at room temperature for 18 hours and then filtered. By IR, both precipitates were identical and were combined and air dried, mp 216-220°C, 58.5 g (88% yield based on cyclohexanone). IR (nujol) 1690 cm^{-1} .

Preparation of 2,5-bis(spirocyclohexyl)imidazolidin-4-one-1-oxyl

- 10 An acetone solution of 260 ml of 0.08M dimethyldioxirane (0.0208 mol), prepared as above, was treated with 2.3 g of 2,5-bis(spirocyclohexyl)imidazolidin-4-one dissolved in 75 ml of chloroform (previously freed of ethanol preservative by washing with 2x20 ml water and drying over magnesium sulfate) and allowed to react at room temperature
- 15 overnight. The preparation was repeated using 1.7 g of amide and 270 ml of 0.0721 M dimethyldioxirane solution. Removal of the ethanol preservative is necessary to prevent the ethanol from being oxidized to acetaldehyde by the dimethyldioxirane/nitroxide system. The solvent was removed on the rotary evaporator, the residue (4.2 g) dissolved in 400 ml hot benzene, filtered to remove
- 20 a trace of insoluble material, the filtrate reduced to 100 ml, rewarmed to bring all the crystals into solution, and allowed to crystallize overnight at room temperature. The yellow crystals were collected by filtration and dried in an oven at 75°C for 10 hours to give 2.4 g of nitroxide, mp 178-183°C. IR (nujol) 1707 cm^{-1} .

25	combustion analysis:	calcd. for $\text{C}_{13}\text{H}_{21}\text{N}_2\text{O}_2$	obs.
	C	65.79	65.67
	H	8.92	8.84
	N	11.80	11.71
	O	13.48	13.31

30

Examples 39-42

Synthesis of N-substituted imidazolidinone nitroxides

The following Examples 39-42 illustrate the process for synthesis of novel nitroxides (1, X=Alkyl).

5 The novel N-substituted imidazolidinone nitroxides were prepared according to the following general procedure.

 A suspension of imidazolidinone nitroxide (5.5 mmol NO-67 or 1.69 mmol NO-88) and sodium hydride (1.33 molar eq., 80% dispersion in oil) was allowed to stir under an atmosphere of nitrogen in acetonitrile solvent (20 ml for NO-67 or 10 ml for NO-88) at room temperature for 15 minutes, and then added the required amount of an alkyl halide (1.20 molar equivalents). After workup and purification by column chromatography, the corresponding new N-substituted imidazolidinone nitroxide was generally obtained in good to excellent yield (45-93%).

15

Example 39

Preparation of 2,5-Bis(spirocyclohexyl)-3-methylimidazolidin-4-one-1-oxyl (NO-88-Me)

20 The title compound, NO-88-Me was isolated as a yellow solid after column chromatography (Kieselgel-60, 70-230 mesh, ethyl acetate/n-hexane 1:4 as eluent) (89.7% yield). Melting point, 103-105°C. MS (CI): 252 (M+1, 100%), 251 (M⁺, 30.7), 237 (87.6), 236 (12.3), 235 (29.3), 222 (24.5), 221 (40.6), 196 (18.7), 193 (10.5), 142 (24.7), 140 (53.9), 112 (16.0) and 99 (23.5).

25

Example 40

Preparation of 2,5-Diethyl-2,3,5-trimethylimidazolidin-4-one-1-oxyl (NO-67-Me)

30 The title compound, NO-67-Me was isolated (45.6% yield) after column chromatography (Kieselgel-60, 70-230 mesh, ethyl acetate/n-hexane 1:3 as eluent) as a yellow liquid. MS (CI): 200 (M+1, 43.0%), 199 (M⁺, 16.0), 186 (23.5), 185 (40.0), 171 (58.0), 170 (34.0), 155 (23.0), 149 (20.2), 141 (11.6), 140 (15.6), 128 (10.0), 126 (16.1), 116 (13.7), 112 (14.4), 111 (12.7), 100 (12.2), 73 (52.0).

Example 41**Preparation of 2,5-Diethyl-2,5-dimethyl-3-benzylimidazolidin-4-one-1-oxyl (NO-67-Bn)**

The title compound, NO-67-Bn was isolated (93.0% yield) after column chromatography (Kieselgel-60, 70-230 mesh, ethyl acetate/n-hexane 1:5 as eluent) as a yellow solid. Melting point, 64-65°C. MS (CI): 276 (M+1, 56.7%), 275 (M⁺, 22.0), 262 (22.0), 261 (100.0), 247 (62.6), 245 (M - NO, 26.0), 231 (86.0), 218 (5.3), 190 (12.3), 170 (15.0), 162 (24.6), 126 (20.1), 102 (4.0), 91 (21.5) and 72 (4.0).


Example 42**Preparation of 2,5-Diethyl-2,5-dimethyl-3-n-butylimidazolidin-4-one-1-oxyl (NO-67-nBu)**

The title compound, NO-67-nBu was isolated (87.0% yield) after column chromatography (Kieselgel-60, 70-230 mesh, ethyl acetate/n-hexane 1:9 as eluent) as a yellow liquid. MS (CI): 242 (M+1, 74.0%), 241 (M⁺, 38.3), 227 (100.0), 213 (86.7), 211 (45.0), 198 (12.0), 197 (88.0), 184 (M - nBu, 7.6), 170 (27.0), 156 (16.3), 128 (27.0), 126 (30.0), 116 (4.3), 98 (8.0) and 72 (7.6).

Example 43**Synthesis of Alkoxyamine of Formula (3)****Preparation of 1-(2-tert-butoxy-1-phenylethoxy)-2,5-bis(spirocyclohexyl)-3-methylimidazolidin-4-one**

The title alkoxyamine, 1-(2-tert-butoxy-1-phenylethoxy)-2,5-bis(spirocyclohexyl)-3-methylimidazolidin-4-one was prepared by treating 1-(2-tert-butoxy-1-phenylethoxy)-2,5-bis(spirocyclohexyl)-imidazolidin-4-one alkoxyamine (m.p. 244-247°C, obtained from the reaction of di-tert-butyl peroxyoxalate, styrene and nitroxide NO-88) with excess methyl iodide in the presence of sodium hydride in dimethyl sulfoxide solvent (Scheme 3). The product was isolated as a white solid in 93% yield, m.p. 129-131°C (aq. MeOH). The alkoxyamine product has improved solubility versus its non-methylated alkoxyamine and is readily soluble in common organic solvents such as ethyl acetate, chloroform, acetone, hot methanol. ¹H-NMR (CDCl₃) δ (ppm) 0.40-2.60 (m, 20H, cyclohexyl-CH₂), 1.10 (s, 9H, tert-butyl-CH₃), 2.90 (s, 3H, N-CH₃), 3.30 (dd, 1H, (CH₃)₃COCH), 3.66 (dd, 1H, (CH₃)₃COCH), 4.69 (dd, 1H, CH(Ph)ON) and 7.25 (br s, 5H, phenyl-H).


Scheme 3



a) NaH / DMSO, excess methyl iodide, at room temperature.

Claims:

1. A polymer of the formula:




wherein:

- 5 R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups in a geminal position with respect to each other can together form a 4-8 membered ring; and R groups in a cis position with respect to each other can together form a 4-8 membered ring;
- 10 X is selected from the group consisting of hydrogen, C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; acyl; X and R can form a 5-8 membered ring; and X and R³ can form a 5-8 membered ring;
- M is one or more monomer units selected from the group consisting of styrene, substituted styrene, alkyl acrylate, alkyl methacrylate, substituted alkyl acrylate, substituted alkyl methacrylate, acrylonitrile, methacrylonitrile, acrylamide, methacrylamide, N-alkylacrylamide, N-alkylmethacrylamide, N,N-dialkylacrylamide, N,N-dialkylmethacrylamide, isoprene and butadiene;
- 15 n is an integer greater than 1;
- Y is a residue derived from a species that initiates free radical polymerization or is selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₁ to C₁₈ alkoxy, substituted C₁ to C₁₈ alkoxy, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl, C₆ to C₁₈ aryloxy, C₆ to C₁₈ substituted aryloxy; and
- 20 all substituents are independently selected from the group that consists of epoxy, hydroxy, C₁ to C₁₈ alkoxy, acyl, acyloxy, alkoxycarbonyl, aryloxycarbonyl, cyano, silyl, halo, and C₁ to C₁₈ dialkylamino.
- 25

2. A process for preparing the polymers of Claim 1 comprising contacting reactant (i) with one or both of reactants (ii) and (iii) wherein:


(i) is at least one monomer M;

5 (ii) is at least one nitroxide of Formula (1)



and a source of free radicals Y•; and

(iii) is at least one alkoxyamine selected from the formula



10 wherein:

R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups in a geminal position with respect to each other can together form a 4-8

15 membered ring; and R groups in a cis position with respect to each other can together form a 4-8 membered ring;

X is selected from the group consisting of hydrogen, C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; acyl; X and R can form a 5-8 membered ring; and X and R³ can form a 5-8 membered ring;

M is one or more monomer units selected from the group consisting of styrene.

20 substituted styrene, alkyl acrylate, alkyl methacrylate, substituted alkyl acrylate.

substituted alkyl methacrylate, acrylonitrile, methacrylonitrile, acrylamide, methacrylamide, N-alkylacrylamide, N-alkylmethacrylamide, N,N-dialkylacrylamide, N,N-dialkylmethacrylamide, isoprene and butadiene;

- Y is a residue derived from a species that initiates free radical polymerization or is selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₁ to C₁₈ alkoxy, substituted C₁ to C₁₈ alkoxy, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl, C₆ to C₁₈ aryloxy, C₆ to C₁₈ substituted aryloxy, (C₁ to C₁₈ alkoxy)carbonyloxy, (C₆ to C₁₈ aryloxy)carbonyloxy, and sulfate radical anions; all substituents are independently selected from the group that consists of epoxy, hydroxy, C₁ to C₁₈ alkoxy, acyl, acyloxy, alkoxycarbonyl, aryloxy, cyano, silyl, halo, and C₁ to C₁₈ dialkylamino;

Z is a group having at least one carbon atom and is such that the carbon centered radical Z• is capable of initiating free radical polymerization of the monomer (M); and


- Y and the reaction conditions are selected so that the Y(M)_n-O moiety in the compounds of Formula (2) formed from reactants (i) and (ii) undergo facile homolysis;

Z and the reaction conditions are selected so that the Z-O moiety and the Z(M)_n-O moiety formed by reacting (i) and (iii) undergo facile homolysis;

and

n is an integer of 1 or greater.


3. Nitroxides of the formula



wherein:


- R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups in a geminal position with respect to each other can together form a 4-8 membered ring; and R groups in a cis position with respect to each other can together form a 4-8 membered ring; and
- 5 X is selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; acyl; X and R can form a 5-8 membered ring; and X and R³ can form a 5-8 membered ring; with the proviso that at least one of R, R¹, R², R³ and X is not methyl.
- 10

4. A nitroxide of Claim 3 selected from the group:



Formula (4)


where X is selected from the group consisting of alkyl, optionally substituted alkyl, benzyl; and



Formula (5)

15 where X is alkyl of C₁ to C₁₈.

5. An alkoxyamine of the formula



wherein:

- 5 R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups in a geminal position with respect to each other can together form a 4-8 membered ring; and R groups in a cis position with respect to each other can together form a 4-8 membered ring;
- 10 X is selected from the group consisting of hydrogen, C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; acyl; X and R can form a 5-8 membered ring; X and R³ can form a 5-8 membered ring; and
- Z is a group having at least one carbon atom and is such that the carbon centered radical Z• is capable of initiating free radical polymerization of the monomer (M).

15

6. An alkoxyamine of Claim 5 wherein Z is selected from the group consisting essentially of -C(Me)₂Ph, -C(Me)₂CN, -C(Me)(CN)CH₂CH(Me)₂, -C(Me)(CN)(substituted alkyl), -C(Me)₂CO₂Alkyl, -C(Me)₂CO₂H, -C(Me)₂CH₂C(Me)₃, -C(Me)₃, -C(Me)HPh and Y(M)ₙ;


20 wherein:

Y is a residue derived from a species that initiates free radical polymerization or is selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₁ to C₁₈ alkoxy, substituted C₁ to C₁₈ alkoxy, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl, C₆ to C₁₈ aryloxy, C₆ to C₁₈ substituted aryloxy, (C₁ to C₁₈ alkoxy)carbonyloxy, (C₆ to C₁₈ aryloxy)carbonyloxy, and sulfate radical anions;

25 and

all substituents are independently selected from the group that consists of epoxy, hydroxy, C₁ to C₁₈ alkoxy, acyl, acyloxy, alkoxycarbonyl, aryloxy, carbonyl, cyano, silyl, halo, and C₁ to C₁₈ dialkylamino.

- 5 7. A method for making the nitroxide of Formula (1):



wherein:

- R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups that are in a geminal position with respect to each other can together form a 4-8 membered ring, and R groups that are in a cis position with respect to each other can together form a 4-8 membered ring;
- X is selected from the group consisting of hydrogen, C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; acyl; X and R can form a 5-8 membered ring; X and R³ can form a 5-8 membered ring;

- comprising the steps: (i) preparing a colorless aqueous ammonium sulfide solution containing sodium thiocyanate by titrating an aqueous ammonium sulfide solution containing ammonium polysulfide with sodium cyanide under nitrogen; (ii) sequentially adding an aminonitrile and a ketone to the aqueous ammonium sulfide solution under nitrogen; (iii) adding base and then neutralizing; and (iv) oxidizing the reaction product of step (iii) to form the nitroxide.

8. The method of Claim 7 wherein:
- R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups in a geminal position with respect to each other can together form a 4-8

- membered ring; and R groups in a cis position with respect to each other can together form a 4-8 membered ring; and
- X is selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; acyl; or X and R can form a 5-8 membered ring; and X and R³ can form a 5-8 membered ring; with the proviso that at least one of R, R¹, R², R³ and X is not methyl.


9. The method of Claim 7 comprising stopping the process before step (iv) and isolating the reaction product of step (iii), and then practicing step (iv).

10. The method of Claim 7 without intermediate isolation of the reaction product of step (iii) before the reaction in step (iv).

11. A colorless aqueous ammonium sulfide solution containing sodium thiocyanate and substantially no ammonium polysulfide.


12. A method for making an alkoxyamine of Claim 5 comprising one of steps (i) to (iii):

- (i) adding Z• to the nitroxide



Formula (1)

- (ii) adding Z-O to the amine



(iii) alkylating the hydroxylamine derived from a nitroxide of Formula (1);

wherein:

- 5 R, R¹, R², R³ are each independently selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; R groups in a geminal position with respect to each other can together form a 4-8 membered ring; and R groups in a cis position with respect to each other can together form a 4-8 membered ring;
- 10 X is selected from the group consisting of C₁ to C₁₈ alkyl, substituted C₁ to C₁₈ alkyl, C₆ to C₁₈ aryl, C₆ to C₁₈ substituted aryl; acyl; X and R can form a 5-8 membered ring; and X and R³ can form a 5-8 membered ring; and
- Z is a group having at least one carbon atom such that the carbon centered radical Z• is capable of initiating free-radical polymerization of monomer (M).

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 4/00, 2/38, C07D 233/38, 235/02	A3	(11) International Publication Number: WO 98/30601 (43) International Publication Date: 16 July 1998 (16.07.98)
(21) International Application Number: PCT/US98/00601 (22) International Filing Date: 7 January 1998 (07.01.98) (30) Priority Data: 60/034,727 10 January 1997 (10.01.97) US (71) Applicants (for all designated States except US): E.I. DUPONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). COMMONWEALTH SCIENTIFIC AND INDUSTRIAL RESEARCH ORGANIZATION [AU/AU]; Bayview Avenue, Clayton, VIC 3168 (AU). (72) Inventors; and (75) Inventors/Applicants (for US only): ANDERSON, Albert, G. [US/US]; 2410 St. Francis Street, Wilmington, DE 19808 (US). GRIDNEV, Alexei [US/US]; 113 Senatorial Drive, Greenville, DE 19807 (US). MOAD, Graeme [AU/AU]; 137 Monbulk Road, Kallista, VIC 3791 (AU). RIZZARDO, Ezio [AU/AU]; 26 Alex Avenue, Wheelers Hill, VIC 3150 (AU). THANG, San, Hoa [AU/AU]; 180 Clarinda Road, Clayton South, VIC 3169 (AU).		(74) Agent: COSTELLO, James, A.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US). (81) Designated States: AU, BR, CA, CN, JP, KR, MX, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> (88) Date of publication of the international search report: 3 December 1998 (03.12.98)
(54) Title: METHOD OF CONTROLLING POLYMER MOLECULAR WEIGHT AND STRUCTURE (57) Abstract This invention concerns the preparation of polymers of low polydispersity and/or controlled molecular weight and architecture employing living free radical polymerization initiated by an alkoxyamine initiator or nitroxide plus, optionally, a free radical initiator; the polymer produced thereby; selected nitroxide and alkoxyamine initiators; and a process for making the initiators; the polymeric products being useful in protective coatings.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP 98/00601

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08F4/00 C08F2/38 C07D233/38 C07D235/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 2 234 294 A (CIBA GEIGY AG) 17 January 1975	3,4
Y	see example 12	1,2
A	see example 1 see claim 1	7
Y	MOAD GRAEME: "Alkoxyamine -initiated living radical polymerization" MACROMOLECULES, 1995, pages 8722-8728, XP002067999 cited in the application see the whole document	1,2
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

15 June 1998

Date of mailing of the international search report

22. 10. 1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,

Authorized officer

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/00601

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 2 311 775 A (CIBA GEIGY AG) 17 December 1976 see claims 1,9 see page 11 see example 1 see page 8	3,4
A	FR 1 528 233 A (SANKYO COMPANY LIMITED) 1968 see the whole document	3,12
P,X	GRIDNEV, ALEXEI A.: "Hydrogen Transfer Reactions of Nitroxides in Free Radical Polymerizations" MACROMOLECULES (1997), 30(25), 7651-7654 CODEN: MAMOBX;ISSN: 0024-9297, XP002068000 see the whole document	1,2
P,A	see TEMIO	3
A	TODA, TOSHIMASA ET AL: "Stable free radicals. VI. Synthesis of substituted 4-imidazolidinone-1-oxyls" BULL. CHEM. SOC. JAP. (1971), 44(12), 3445-50 CODEN: BCSJA8, XP002068001 see page 3447	3,4
A	see page 3445, column 2, paragraph 1 - page 3446, column 2, paragraph 2 see page 3449, column 2, line 9 - line 13 see page 3449, column 2, line 24 - line 27	7

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 98/00601

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

claims 1-10,12

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International Application No. PCT/US 98/00601

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

1. Claims: 1-10,12

Polymer containing a nitroxide of formula (1), Process for preparing it, Nitroxides of formula (1) or Alkoxyamine of formula (2) generating them and Processes for preparing (1) or (2).

The technical feature linking all these previous claims is the structure (1).

2. Claim : 11

Colorless aqueous ammonium sulfide solution.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/00601

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2234294 A	17-01-1975	CH 579117 A	31-08-1976
		BE 816695 A	23-12-1974
		DE 2427853 A	16-01-1975
		DK 336574 A	24-02-1975
		GB 1453099 A	20-10-1976
		IE 39301 B	13-09-1978
		JP 50088142 A	15-07-1975
		LU 70361 A	31-05-1976
		NL 7408217 A	24-12-1974
		US 3971757 A	27-07-1976
FR 2311775 A	17-12-1976	DE 2621947 A	09-12-1976
		JP 51149272 A	22-12-1976
FR 1528233 A	08-11-1968	DE 1695737 A	22-04-1971
		GB 1194402 A	10-06-1970
		US 3532703 A	06-10-1970

